

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C08K 5/14, C08L 1/10, C08F 299/04	A1	(11) International Publication Number: WO 95/18180 (43) International Publication Date: 6 July 1995 (06.07.95)
(21) International Application Number: PCT/EP94/04249 (22) International Filing Date: 21 December 1994 (21.12.94) (30) Priority Data: 93203699.9 27 December 1993 (27.12.93) EP (34) Countries for which the regional or international application was filed: NL et al. (71) Applicant (for all designated States except US): AKZO NOBEL N.V. [NL/NL]; Velperweg 76, NL-6824 BM Arnhem (NL). (72) Inventors; and (75) Inventors/Applicants (for US only): TORENBEEK, Reinder [NL/NL]; Quabbenburgerweg 8, NL-7396 NN Terwolde (NL). EIJMANS, Jacobus, Johannes, Antonius [NL/NL]; Het Vlier 35, NL-7414 AR Deventer (NL). (74) Agent: SCHALKWIJK, Pieter, Cornelis; Akzo Nobel N.V., Patent Dept. (Dept. APTA), P.O. Box 9300, NL-6800 SB Arnhem (NL).		(81) Designated States: CN, JP, KR, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: GELS OF ORGANIC PEROXIDES (57) Abstract <p>The present invention relates to a gel comprising A) a solution of at least one organic peroxide essentially solubilized in a phlegmatizer, B) at least one cellulose ester as thickening agent essentially solubilized in solution A, and C) at least one thixotropic agent selected from hydrogenated castor oil and fumed silica. These gels offer the advantages of essentially no phase segregation during storage, essentially no formation of solid crystals during storage, and easy metering into thermoset resins because of their thixotropic behaviour. Furthermore, these gels may be transparent, with the advantage that brightly coloured gels may be prepared therefrom.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

Gels of organic peroxides

5 The present invention relates to gels of organic peroxides and the use of said gels in the curing of thermoset resins.

10 The application of organic peroxides in thermoset resins was attended with some problems in the past when mixing small quantities of a liquid or powdered organic peroxide or formulations thereof into the resins. These problems led to the development of organic peroxide paste formulations.

15 In the past, these organic peroxide paste formulations were packaged in tubes. Such packaging would enable a skilled man to meter small quantities into thermoset resins. However, the dispensing still remained troublesome and inaccurate. The introduction of the cartridge some 15 years ago was a breakthrough in this respect. Nowadays, these cartridges comprising an organic peroxide paste formulation vary from
20 very simple hand-operated types to automatically controlled dispensers adjusting the organic peroxide dosing level to regulate the curing speed.

25 The use of these cartridges requires certain properties of the organic peroxide paste formulations, such as no separation of liquid from the formulation and consequent leakage from the cartridge and no unwanted discharge of the paste from open cartridges.

30 It has now been found that the presently known organic peroxide paste formulations do not perform as required in cartridges.

Netherlands patent application 70 06273 discloses a transparent paste comprising an organic peroxide, a phlegmatizer, and a gel-forming

agent, e.g., hydrogenated castor oil. US patents 3,806,477 and 3,859,240 disclose pastes comprising a ketone peroxide, a phlegmatizer, and a gel-forming colloid, e.g., a cellulose ester or a silica aerogel. No mention is made of mixtures of the exemplified
5 gel-forming colloids. US patent 3,795,630 discloses stable peroxide compositions comprising an organic peroxide, a phlegmatizer in which the organic peroxide is not soluble, and a hydrophobic, alkyl groups containing silicon dioxide. U.S. patent 3,507,800 discloses
10 compositions comprising organic peroxides, water, and a mutual solvent, which may be, among others, a phlegmatizer or a gel-forming material. German patent 1,567,857 discloses coloured pastes comprising organic peroxides, phlegmatizers, gelling agents, such as cellulose ethers, and a pigment. Finally, U.S. patent 3,182,026 discloses also a
15 coloured organic peroxide composition comprising organic peroxides, phlegmatizer, pigment, and a gel-forming colloid, such as alkyl cellulose or finely divided silica.

These known pastes either are storage unstable, i.e., liquid separation occurs, and/or their thixotropic behaviour is such that
20 dosing small quantities from a cartridge is difficult if not impossible.

Accordingly, one object of the present invention is to provide a composition comprising an organic peroxide which is storage stable.
25 Another object is to provide a composition which has thixotropic properties.

The present invention relates to a gel comprising
30 A) a solution of at least one organic peroxide essentially solubilized in a phlegmatizer,
B) at least one cellulose ester as thickening agent essentially solubilized in solution A, and
C) at least one thixotropic agent selected from hydrogenated castor oil and fumed silica.

These gels offer the advantages of essentially no phase segregation during storage and easy metering into thermoset resins because of their thixotropic behaviour. Furthermore, the organic peroxide is essentially solubilized. So, essentially no solid crystals are present in the composition and there is no crystal growth on storage.

5

Examples of organic peroxides to be used in the compositions of the present invention include hydroperoxides, such as cumene hydroperoxide; diacyl peroxides, such as, optionally substituted, dibenzoyl peroxide; peroxyester, such as tert-butyl peroxy benzoate and tert-butyl peroxy 2-ethylhexanoate; peroxyketals, such as 10 1,1-bis(tert-butylperoxy)-3,3,5-trimethylcyclohexane; and ketone peroxides, such as cyclohexanone peroxide, acetone peroxide, acetyl acetone peroxide, methyl ethyl ketone peroxide, and methyl isobutyl ketone peroxide. Preferred are ketone peroxides.

15

The phlegmatizers to be used in the compositions of the present invention have to be able to solubilize the ketone peroxide and the cellulose ester. Examples of such phlegmatizers include phthalates, such as dimethyl phthalate, diethyl phthalate, dibutyl phthalate, 20 diisobutyl phthalate, and butyl benzyl phthalate; glycols, such as diethylene glycol, propylene glycol, and diacetone alcohol; citrates, such as acetyl tributyl citrate; benzoates, such as ethylene glycol dibenzoate and propylene glycol dibenzoate; phosphates, such as triethyl phosphate and tributyl phosphate; acid esters, such as esters of adipic acid, glutaric acid, maleic acid, fumaric acid, and succinic acid; 25 butyrates, such as 2,2,4-trimethyl-1,3-pentanediol diisobutyrate; and mixtures thereof. The amount of phlegmatizer present in the composition of the present invention is preferably between 5 and 95 wt%, more preferably between 40 and 85 wt%, based on the total weight of the composition.

30

The cellulose ester used in the compositions of the present invention is soluble in the solution of peroxide and phlegmatizer and raises the

viscosity of the composition. Cellulose esters are the reaction product of cellulose and acid compounds. Examples of such acid compounds include acetic acid, propionic acid, butyric acid, phthalic acid, trimellitic acid, and mixtures thereof. Preferred is a cellulose ester where the cellulose is esterified with a mixture of acetic acid and butyric acid. The amount of cellulose ester present in the composition is preferably between 0.5 and 10 wt%, more preferably between 1 and 4 wt%, based on the total weight of the composition.

The thixotropic agent is selected from hydrogenated castor oil and fumed silica.

The hydrogenated castor oil used in the compositions of the present invention swells in the composition to form a gel structure that prevents the liquid from flowing unless shear forces are applied and the structure breaks down, i.e., when the composition is squeezed out of the cartridge. Examples of commercially available products are Rheocin® (ex Süd Chemie), Thixcin® (ex Rheox Inc.), and Luvotix® (ex Lehmann & Voss). The amounts of hydrogenated castor oil present in the composition of the present invention range preferably from 0.2 to 7 wt%, more preferably from 0.5 to 4 wt%, based on the total weight of the composition.

Fumed silica is obtained by flame hydrolysis of SiCl_4 . It is a very pure SiO_2 and due to the absence of impurities it is the only inorganic thixotropic agent to be used in the present transparent gels. Examples of commercially available fumed silica include Aerosil® (ex Degussa), Cab-O-Sil® (ex Cabot), and HDK® (ex Wacker). The amounts of fumed silica present in the composition are preferably from 1 to 10 wt%, more preferably from 2 to 7 wt%, based on the total weight of the composition.

The stability and the application properties of the compositions of the present invention may be improved or adapted by known additives

such as sequestering agents, e.g. dipicolinic acid, and antioxydants, e.g., phenolic compounds such as 2,6-di(tert-butyl)-4-methyl phenol and para-nonyl phenol.

5 Optionally, a solvent may be present in the composition of the present invention. The solvent has to be sufficiently compatible with the other compounds in the composition not to affect the solubility of the organic peroxide and the cellulose ester in the phlegmatizer. Examples of such solvents include water, ketones, alcohols, cumene, and esters.

10 The active oxygen content of the gels of the present invention is between 1 and 10%.

15 Although the present invention is not limited to transparent gels, these are the preferred gels. More particularly, because the pigment or dye is not hidden by any solid material as would be the case with non-transparent gels, transparent gels may be intensely bright in colour when coloured by blending in pigments or dyes. Furthermore, less pigment or dye is necessary than in the preparation of a coloured non-transparent gel. Preferred are organic pigments such as azo
20 condensation pigments and indanthrones. Brightly coloured gels are particularly suitable for facilitating mixing into thermoset resins because they can easily be traced and, accordingly, a homogeneous mixture of resin and peroxide formulation can be obtained.

25 The sequence in which the compounds are added is not essential to the preparation of the gels of the present invention. Often, the organic peroxide is purchased in a liquid formulation together with a phlegmatizer for safety reasons. The cellulose ester and the thixotropic agent may be mixed with the organic peroxide solubilized
30 in the phlegmatizer. It is also possible to dissolve the cellulose ester and to disperse the thixotropic agent in a phlegmatizer. The resulting mixture can be added to the organic peroxide, which may already be solubilized in phlegmatizer. High shear mixers may be used

to prepare the gel. Optionally, the composition may be aged to enhance its thixotropic behaviour.

5 The gels of the present invention may be used in the curing of thermoset resins, such as unsaturated polyester resins or vinyl ester resins. Unsaturated polyester resins have found a wide range of applications in the automotive industry, in car-repair shops, and in do-it-yourself jobs. Furthermore, both of the exemplified resins may be applied in the preparation of castings and laminates.

10 The invention will be further illustrated by the following examples which are not to be construed as limiting the invention in any way. The scope of the invention is to be determined from the claims appended hereto.

15 Examples

The following materials were applied in the examples:

Trigonox® HM	Methyl isobutyl ketone peroxide in phthalate, ex Akzo Chemicals
20 Trigonox® 113	Cyclohexanone peroxide in phthalate, ex Akzo Chemicals
Butanox® M50	Methyl ethyl ketone peroxide in phthalate, ex Akzo Chemicals
25 Trigonox® 44B	Acetyl acetone peroxide in diacetone alcohol + diethylene glycol, ex Akzo Chemicals
Trigonox® K-80	Cumenehydroperoxide 80% in alcohol, ex Akzo Chemicals
Trigonox® C-B75	Tert-butylperoxy benzoate 75% in phthalate, ex Akzo Chemicals
30 Trigonox® 29	1,1-bis(tert-butylperoxy)-3,3,5-trimethylcyclohexane, ex Akzo Chemicals
CAB® 381-20	Cellulose acetate/butyrate (13%/37%); Mn = 70 000, ex Eastman Chemicals
CAB® 381-2	Cellulose acetate/butyrate (13%/37%); Mn = 40 000, ex Eastman Chemicals

CAB® 500-5	Cellulose acetate/butyrate (4%/51%), ex Eastman Chemicals
CAB® 531-1	Cellulose acetate/butyrate (2.8%/50%), ex Eastman Kodak
Rheocin® R	Hydrogenated castor oil, ex SudChemie AG
Thixcin® R	Hydrogenated castor oil, ex Rheox Inc.
HDK®-N20	Fumed silica, ex Wacker
Kodaflex® TXIB	2,2,4-trimethyl-1,3-pentanediol diisobutyrate, ex Eastman Kodak

10 Example 1

15 A solution of cyclohexanone peroxides was prepared by reacting cyclohexanone and H₂O₂ in dimethyl phthalate, washing and removal of the water phase. The solution was stabilized with 100 mg/kg dipicolinic acid. The total active oxygen content was analysed to be 10.0%.

20 Starting with 813 g of this solution a gel was prepared by adding 127 g diisobutyl phthalate, 30 g CAB® 381-20 and 30 g Rheocin® R, respectively, in a vessel stirred with a high-shear mixer. The cellulose ester was dissolved and the hydrogenated castor oil swelled during mixing. After 15 minutes the mixing was stopped. The gel was transparent and thixotropic in behaviour: after 24 hours the viscosity, determined with a Brookfield HB rotational viscometer
25 provided with spindle TB at 1 rev/minute, was 359 Pa.s. After stirring of the gel the viscosity was 196 Pa.s.

30 The active oxygen content was 6.5%. The gel was stored for 6 months at 20°C. During this period no separation of liquid from the gel was observed. The relative loss of active oxygen was only 0.9%.

Comparative Examples A-D

According to the procedure as used in Example 1 compositions were prepared with the following formulation.

5

Example	A	B	C	D
Cyclohexanone peroxide solution (see example 1)	813 g	813 g	813 g	813 g
10 CAB® 381-20	30 g	60 g	-	-
Rheocin® R	-	-	30 g	60 g
Diisobutyl phthalate	157 g	127 g	157 g	127 g

15

The viscosity of the compositions of Examples A to D was determined with a Brookfield HB rotational viscometer provided with spindle TB at 1 rev/minute. The compositions of Examples A and B were transparent, fluid liquids with a viscosity of 6 Pa.s and 83 Pa.s, respectively. Due to the low viscosity without cellulose ester the preparation of the compositions of Examples C and D required twice the mixing time of Example 1. The composition of Example C was a white turbid liquid with a viscosity of 27 Pa.s. On storage it showed segregation of a clear liquid amounting to 45 ml per 400 g composition after 4 weeks at 20°C. The composition of Example D resulted in a white, semi-transparent gel with a thixotropic structure. The viscosity (after 24 h storage) was 432 Pa.s, after stirring it was 262 Pa.s. On storage the gel showed syneresis, i.e., expulsion of liquid, 0.5 ml per 400 g gel after 4 weeks at 20°C.

20

25

30

An advantage of the combination of the thickening and the thixotropic agent is the improved behaviour of the gel in cartridges. Those cartridges consist of a rigid plastic tube closed with a cap at one side and fitted with a piston at the other side. The gel is dosed by removing the cap, moving the piston over a preset distance with the dosing machine, and removing the gel that is extruded from the tube.

To show the difference in suitability, cartridges were filled with the compositions of Examples 1, B, and D, respectively. The cartridges were stored in a horizontal position in cardboard boxes. The composition of Example B passed through the piston as well as the cap and contaminated the cardboard. After removal of the cap all of the composition flowed from the cartridge as it lacked a thixotropic structure. In the composition of Example D some liquid was separated out by syneresis of the gel. This liquid passed through the piston and contaminated the cardboard. The gel of Example 1 neither separated nor showed any dripping after removal of the cap. It could be dosed without any problem.

Examples 2-6

The following examples show that the invention is applicable to different types of organic peroxides. The following compositions were prepared:

	Example	2	3	4	5	6
	Trigonox® HM	818	940	-	-	-
	Trigonox® 113	-	-	940	-	-
10	Butanox® M50	-	-	-	950	818
	Diisobutyl phthalate	122	-	-	-	122
	CAB® 381-20	30	30	30	-	30
15	CAB® 381-2	-	-	-	30	-
	Rheocin® R	30	30	30	20	30
	Active oxygen %	7.2	8.2	7.0	8.5	7.3
	Viscosity Pa.s	170	186	192	150	112
20	Viscosity after stirring Pa.s	122	115	96	80	67

The viscosity was determined with a Brookfield HB rotational viscometer provided with spindle TB at 1 rev/minute. All formulations were transparent gels with a thixotropic structure, as is demonstrated by the viscosity figures before and after stirring.

Example 7 and Comparative Examples E-F

In the same way as in Example 1, gels were prepared with fumed silica as the thixotropic agent.

Example	E	7	F
Cyclohexanone peroxide solution (see example 1)	813	813	813
CAB® 381-20	-	20	-
HDK®-N20	50	30	30
Diisobutyl phthalate	137	137	157

The viscosity was determined with a Brookfield HB rotational viscometer provided with spindle TB at 1 rev/minute. The composition of Example E was a thixotropic composition, with a viscosity of 461 Pa.s 1 day after preparation and of 125 Pa.s after breakdown of the structure by stirring. On storage some clear liquid was separated out, approximately 2 ml per 400 g composition after 4 weeks. The composition of Example 7 had a lower viscosity, 128 Pa.s, and 32 Pa.s, after stirring, but it did not show separation within 4 weeks. The composition of Example F was a thick, fluid liquid and separated out approximately 4 ml per 400 g composition of thin liquid within 4 weeks.

The composition of Example F was not suitable to be packed either in tubes or in dosing cartridges, the composition of Example E was only suitable for packing into tubes with a sealed end. It could not be packed into cartridges because of leakage of migrating liquid. The composition of Example 7 was suitable for both tubes and cartridges.

These examples show that, as regards the quality of the paste, thickening with the combination of cellulose ester and silica has advantages over thickening with silica alone.

Example 8

A coloured gel was prepared in the same manner as described in Example 1 by mixing 930 g Triganox[®] 113, 30 g CAB[®] 381-20, 30 g Rheocin[®] R, 5 g p-nonylphenol, 0.1 g dipicolinic acid, and 5 g indanthrone, a blue organic pigment. The viscosity was determined with a Brookfield HB rotational viscometer provided with spindle TB at 1 rev/minute. The gel was thixotropic in behaviour: the viscosity was 77 Pa.s, after stirring it was 45 Pa.s. The active oxygen content was 6.98%. On storage no separation was observed after 8 weeks at 20°C.

Examples 9-11

The following examples show that the invention is applicable to formulations comprising acetyl acetone peroxide. The compositions were aged for 56 days. The viscosity was determined with a Brookfield HB rotational viscometer provided with spindle TB at 1 rev/minute.

Example	9	10	11
Trigonox® 44B	813	557	548
Dimethyl phthalate	122	370	365
CAB® 381-20	30	-	-
CAB® 500-5	-	40	39
Rheocin® R	30	29	-
HDK®-N20	-	-	45
Dipicolinic acid	0.1	0.05	0.05
p-nonyl phenol	5	4	3
Active oxygen %	3.2	2.2	2.2
Viscosity Pa.s	32	32	282
Viscosity after stirring Pa.s	6	16	67
aged for 56 days			
Viscosity Pa.s	553	418	-
Viscosity after stirring Pa.s	228	138	-

Example 12

625 g Trigonox® K-80 was mixed up with 325 g Kodaflex® TXIB and 20 g CAB® 381-20. 30 g Rheocin® R was added and dispersed with a high shear mixer. A transparent gel was obtained with a thixotropic structure:

the viscosity (Brookfield HB, spindle TB, at 1 rpm) was 436 Pa.s. After stirring of the gel the viscosity was 190 Pa.s. After eight weeks storage at 20°C the viscosity of the gel had not changed.

Example 13

5

950 g Trigonox® C-B75 was mixed up with 20 g CAB® 381-20 and stirred until the solution was clear. 30 g Rheocin® R was added and dispersed with a high shear mixer. A nice transparent thixotropic gel was obtained with a viscosity (Brookfield HB, spindle TB, at 1 rpm) of 323 Pa.s and after stirring of the gel 214 Pa.s. After eight weeks storage at 20°C the gel showed no separation. The viscosity had not changed.

10

Example 14

15

40 g CAB® 531-1 was dissolved in 394 g dibutylphthalate at 80°C. The solution was cooled and 526 g Trigonox® 29 was admixed. Finally 40 g Thixcin® R was added and dispersed. A transparent gel was the result with a viscosity of 267 Pa.s after 1 day storage (Brookfield HB, spindle TB, at 1 rpm). After stirring the viscosity was 129 Pa.s. After eight weeks storage at 20°C the gel showed no separation. The viscosity had not changed.

20

25

30

Claims

1. A gel comprising
 - A) a solution of at least one organic peroxide essentially solubilized in a phlegmatizer,
 - B) at least one cellulose ester as thickening agent essentially solubilized in solution A, and
 - C) at least one thixotropic agent selected from hydrogenated castor oil and fumed silica.
2. Gel according to claim 1, characterized in that said organic peroxide is a ketone peroxide.
3. Gel according to claim 2, characterized in that the organic peroxide is selected from the group of cyclohexanone peroxide, acetone peroxide, acetyl acetone peroxide, methyl ethyl ketone peroxide, and methyl isobutyl ketone peroxide.
4. Gel according to any one of the preceding claims, characterized in that said phlegmatizer is selected from the group of phthalates, glycols, citrates, benzoates, phosphates, acid esters, butyrates, and mixtures thereof.
5. Gel according to claim 4, characterized in that said phlegmatizer is selected from the group of dimethyl phthalate, diethyl phthalate, dibutyl phthalate, diisobutyl phthalate, butyl benzyl phthalate, diethylene glycol, propylene glycol, diacetone alcohol, acetyl tributyl citrate, ethylene glycol dibenzoate, propylene glycol dibenzoate, triethyl phosphate, tributyl phosphate, adipic acid ester, glutaric acid ester, maleic acid ester, fumaric acid ester, succinic acid ester, 2,2,4-trimethyl-1,3-pentanediol diisobutyrate, and mixtures thereof.

6. Gel according to any one of the preceding claims, characterized in that said cellulose ester is the reaction product of cellulose and at least one acid compound whereby said acid compound is selected from the group of acetic acid, propionic acid, butyric acid, phthalic acid, trimellitic acid, and mixtures thereof.

5

7. Gel according to claim 6, characterized in that said acid compound is selected from acetic acid, butyric acid, and mixtures thereof.

10

8. Gel according to any one of the preceding claims, characterized in that said gel is coloured.

9. Use of gels according to any one of claims 1 to 8 in the hardening of thermoset resins.

15

10. Use according to claim 9, characterized in that the thermoset resin is unsaturated polyester resin.

20

25

30

INTERNATIONAL SEARCH REPORT

Int .onal Application No
PCT/EP 94/04249A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C08K5/14 C08L1/10 C08F299/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C08K C08F C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 299 917 (HILTI AG) 18 January 1989 see column 3, line 64 - column 4, line 1 ---	1
A	CHEMICAL ABSTRACTS, vol. 82, no. 20, 19 May 1975 Columbus, Ohio, US; abstract no. 126278h, 'decorative panels' page 51; see abstract & JP,A,74 102 779 (NIPPON SYNTHETIC CHEM IND KK) 31 January 1973 -----	1

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

31. March 1995

Date of mailing of the international search report

26. 04. 95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Schueler, D

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 94/04249

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0299917	18-01-89	DE-A- 3723088	26-01-89
		DE-A- 3871269	25-06-92
		JP-A- 1038488	08-02-89
		US-A- 4982878	08-01-91
